

OK to Enter  
1



09/15/25375 NE  
Sub App  
#4  
SUBSTITUTE SPECIFICATION

FIELD EMISSION DISPLAY AND METHOD OF FABRICATING SAME

RECEIVED

OCT - 4 2000  
TECHNOLOGY CENTER 2800

5

BACKGROUND OF THE INVENTION

(a) Field of the Invention

The present invention relates to a field emission display and a method of fabricating the same and, more particularly, to a field emission display which effectively enhances electron emitting characteristics.

(b) Description of the Related Art

Generally, field emission displays (FEDs) are display devices where electrons are liberated from an emitter on a cathode by quantum mechanical tunneling and impinge upon phosphors on an anode, thereby producing a predetermined screen image.

A tip-based emitter and a broad area emitter may be used for such an emitter. The tip-based emitter is provided with a gate electrode, and electrons are emitted from the tip-based emitter due to differences in the applied voltages to the cathode and the gate electrode. In contrast, the broad area emitter does not have such a gate electrode, and electrons are emitted from the broad area emitter due to differences in the applied voltages to the cathode and the anode.

The tip-based emitter is prepared by forming an insulating layer and a gate electrode on the cathode, etching the insulating layer and the gate electrode, and depositing an electron emitting material such as molybdenum and silicon onto the etched space. The resulting tip-based emitter is provided with a large number of micro-tips corresponding to pixels.

However, due to the micro-tip structure of the tip-based emitter, it becomes difficult to uniformly form electron emitting

tips over the entire display area and to employ the tip-based emitter for use in large area display devices. Furthermore, such a tip-based emitter is vulnerable to damage and necessarily involves extremely sophisticated tip formation techniques, resulting in increased production cost.

Alternatively, it has been suggested that a broad area emitter, using diamond, diamond-like carbon, graphite particles or carbon fibers, could replace the tip-based emitter with improved electron emitting characteristics.

Particularly, it is known that the carbon fiber-based emitter has a relatively good electron emitting characteristic. Such a carbon fiber-based emitter is usually prepared by cutting and pulverizing carbon fibers to make a carbon fiber powder, adding a frit and a binder to the carbon fiber powder to make an emitter paste, and printing the emitter paste onto a cathode. However, it turns out that the carbon fiber components are non-uniformly distributed over the display area. Such a non-uniform distribution of the carbon fiber components makes it difficult to obtain the desired electron emitting effect. This is presumably because the pointed end portion of the carbon fiber has a locally intensified electron emitting property and, due to the non-uniform distribution of the carbon fiber components, the pointed end portion of the carbon fiber cannot be directed toward the display screen.

This problem is also present in the graphite powder-based emitter where plate-shaped graphite particles are disorderly over-layered.

## SUMMARY OF THE INVENTION

It is an object of the present invention to provide a field emission display which can effectively enhance electron emitting characteristics with an emitter having uniformly aligned electron emitting components.

1

These and other objects may be achieved by a field emission display including first and second substrates spaced apart from each other at a predetermined distance. The first substrate has a top surface, and the second substrate has a bottom surface. The top surface of the first substrate faces the bottom surface of the second substrate. A cathode is disposed on the top surface of the first substrate. The cathode has a top surface and a bottom surface. The bottom surface of the cathode contacts the top surface of the first substrate. An anode is disposed on the bottom surface of the second substrate. The anode has a top surface and a bottom surface. The top surface of the anode contacts the bottom surface of the second substrate. A phosphor screen is formed on the bottom surface of the anode. An emitter is formed on the top surface of the cathode. The emitter faces the phosphor screen.

The emitter includes an electron emission member having a longitudinal dimension, and an alignment member for aligning the electron emission member. The alignment member is formed with a magnetic material. The electron emission member is aligned by the alignment member such that the longitudinal dimension of the electron emission member is vertically extended from the cathode toward the phosphor screen of the anode.

The electron emission member may be formed with carbon fibers or graphite particles. The magnetic material is coated on the carbon fibers or graphite particles. Alternatively, the magnetic material may be incorporated into the internal structure of the carbon fibers or graphite particles.

A method of fabricating the field emission display includes the steps of 1) forming a cathode and an anode each through depositing a conductive layer onto a suitable substrate, 2) preparing an emitter paste through mixing an electron emitting material, a magnetic material and additives such as a frit and a binder, 3) screen-printing the emitter paste onto the cathode, 4) aligning the electron emitting material by forming a magnetic

1  
field in the vicinity of the printed emitter paste such that the  
electron emitting material can be arranged substantially vertical  
to the cathode, 5) solidifying the emitter paste by drying and  
5 burning it, and 6) sealing the substrates into one body.

#### BRIEF DESCRIPTION OF THE DRAWINGS

A more complete appreciation of the invention, and many of  
the attendant advantages thereof, will be readily apparent as the  
10 same becomes better understood by reference to the following  
detailed description when considered in conjunction with the  
accompanying drawings in which like reference symbols indicate  
the same or the similar components, wherein:

15 Fig. 1 is a cross sectional view of a field emission display  
with an emitter according to a preferred embodiment of the  
present invention;

Fig. 2 is an enlarged sectional view of the emitter shown  
in Fig. 1;

20 Fig. 3 is an enlarged sectional view of an emitter for a  
field emission display according to another preferred embodiment  
of the present invention;

Fig. 4 is a processing flowchart sequentially illustrating  
the steps of fabricating the field emission display shown in Fig.  
1; and

25 Fig. 5 is an enlarged sectional view of the emitter shown  
in Fig. 1 illustrating an electron emitting material aligning  
procedure.

#### 30 DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

Preferred embodiments of this invention will be explained  
with reference to the accompanying drawings.

Fig. 1 is a cross sectional view of a field emission display  
according to a first preferred embodiment of the present  
invention. As shown in Fig. 1, the field emission display  
35 includes a first substrate 2 with a top surface, and a second

1 substrate 4 spaced apart from the first substrate 2 at a  
predetermined distance. The second substrate 4 has a bottom  
5 surface facing the top surface of the first substrate 2. A  
cathode 6 is disposed on the top surface of the first substrate  
2, and an anode 8 is disposed on the bottom surface of the second  
substrate 4. The cathode 6 has a plurality of linear electrode  
portions which are arranged parallel to each other, and the anode  
10 8 has another plurality of linear electrode portions. The linear  
electrode portions of the anode 8 are formed to be perpendicular  
to those of the cathode 6.

An emitter 10 is formed on a top surface of the cathode 6,  
and a phosphor screen 12 is formed on a bottom surface of the  
15 anode 8 such that it faces the emitter 10.

15 In this structure, when a predetermined pattern of voltage  
is applied onto the cathode 6 and another predetermined pattern  
of voltage onto the anode 8, the voltage difference between the  
cathode 6 and the anode 8 induces an electric field to be applied  
20 onto the emitter 10. With the application of the electric field,  
electrons (indicated by dotted line arrows in the drawing) are  
liberated from the emitter 10, and impinge upon phosphors on the  
phosphor screen 12, thereby producing a screen image.

Fig. 2 is an enlarged sectional view of the emitter 10. The  
25 emitter 10 is formed with an electron emission member 24 and an  
alignment member 20 for aligning the electron emission member 24.  
The electron emission member 24 is formed with fine pillar-shaped  
carbon fibers. The alignment member 20 is formed with a magnetic  
material that is magnetized under the influence of the magnetic  
30 field. The magnetic material may be selected from Fe, Ni,  $\text{Fe}_2\text{O}_3$ ,  
or Co.

The magnetic material for the alignment member 20 is coated  
on the surface of the carbon fibers for the electron emission  
member 24. Alternatively, the magnetic material for the alignment  
35 member 20 may be incorporated into the internal structure of the  
carbon fibers for the electron emission member 24.

1  
5  
10  
15  
20  
25  
30  
35

With the application of a magnetic field, the alignment member 20 aligns the electron emission member 24 in a predetermined direction. The electron emission member 24 is preferably aligned such that the longitudinal dimension of the electron emission member 24 is vertically extended from the cathode 6 toward the phosphor screen 12 of the anode 8. In this structure, an end portion of the electron emission member 24 is exposed to the vacuum atmosphere and directed toward the phosphor screen 12. The intensified electron emitting characteristic of the end portion of the electron emission member 24 makes it possible to enhance the overall electron emitting characteristic of the emitter 10 even at the same voltage level.

Fig. 3 is an enlarged sectional view of an emitter for a field emission display according to a second preferred embodiment of the present invention. Other components of the field emission display are the same as those related to the first preferred embodiment except that the emitter 10 has a new electron emission member 24'. The electron emission member 24' is formed with plate-shaped graphite particles. With the addition of the alignment member 20, the electron emission member 24 is aligned in a predetermined direction with the same effects as in the first preferred embodiment.

A method of fabricating the field emission display will be specifically described with reference to Figs. 4 and 5.

Fig. 4 is a processing flowchart illustrating the steps of fabricating the field emission display. As shown in Fig. 4, the method of fabricating the field emission display roughly includes the steps of, 1) forming a cathode and an anode each through depositing a conductive layer onto a suitable substrate, 2) preparing an emitter paste through mixing an electron emitting material, a magnetic material and additives such as a frit and a binder, 3) screen-printing the emitter paste onto the cathode, 4) aligning the electron emitting material through forming a magnetic field in the vicinity of the printed emitter paste such

1  
that the electron emitting material can be arranged substantially  
vertical to the cathode, 5) solidifying the emitter paste through  
drying and burning it, and 6) sealing the substrates into one  
5 body.

Specifically speaking, indium tin oxide is first sputtered  
onto the substrate, and etched to thereby form an anode having  
a plurality of linear electrode portions.

10 Red, green and blue phosphors are screen-printed onto the  
anode, and heat-treated to thereby form a phosphor screen. A  
spacer paste is printed in-between the phosphors, and heat-  
treated to thereby form a spacer.

15 Indium tin oxide or silver is sputtered and screen-printed  
onto a substrate to thereby form a cathode having a plurality of  
linear electrode portions. A spacer paste is screen-printed in-  
between the linear electrode portions of the cathode, and heat-  
treated to thereby form a spacer.

20 A magnetic material such as Fe, Ni,  $\text{Fe}_2\text{O}_3$  or Co is plated or  
coated onto carbon fibers for emitting electrons by using a  
technique known in the relevant art. Alternatively, the magnetic  
material may be incorporated into the internal structure of the  
carbon fibers by adding it into precursors of the carbon fibers.

25 The carbon fibers containing the magnetic material are then  
cut and pulverized to thereby form a carbon fiber powder. Then,  
additives such as a frit and a binder are mixed with the carbon  
fiber powder to thereby prepare an emitter paste having a  
predetermined viscosity.

30 The emitter paste is printed onto the cathode in a  
predetermined pattern. The paste printing is performed by a thick  
filming process including a screen printing technique. With the  
application of such a thick filming process, the emitter can be  
easily and uniformly formed with a desired pattern. This means  
35 that the processing steps can be effectively simplified.

1

5

As shown in Fig. 5 where reference numeral 30 indicates the printed emitter paste, a magnetic field B is formed between the bottom and top sides of the printed emitter paste 30. The direction of the magnetic field is established to be perpendicular to the cathode 6.

10

Under the influence of the magnetic field B, the magnetic material component 20 is magnetized to thereby align the carbon fiber components 22 in the direction of the magnetic field B.

Thereafter, the emitter paste 30 is dried and burned to thereby form the emitter 10.

15

The electron emitting material may also be formed with graphite particles. The graphite-based emitter fabricating process is the same as the carbon fiber-based emitter fabricating process except that graphite particles are used instead of carbon fibers.

20

A sealing frit 16 is coated on the edges of the first and second substrates 2 and 4 while leaving a gas exhaust portion. In the sealing process, the plural-lined anode and cathode 6 and 8 are arranged perpendicular to each other and heat-treated under an appropriate pressurizing condition.

25

Thereafter, a vacuum pump is connected to the gas exhaust portion and causes the internal vacuum atmosphere of the substrates to be in the range of  $10^{-4} \sim 10^{-10}$  Torr. Finally, the gas exhaust portion is completely sealed.

30

In this way, the electron emitting material components of the emitter can be aligned substantially perpendicular to the cathode, and the end portions of the electron emitting material components can be exposed to the vacuum atmosphere and directed toward the anode, thereby producing good electron emitting effects.

As described above, the inventive emitter can effectively enhance electron emitting characteristics.

35

While the present invention has been described in detail with reference to the preferred embodiments, those skilled in the



1

art will appreciate that various modifications and substitutions  
can be made thereto without departing from the spirit and scope  
of the present invention as set forth in the appended claims.

5

10

15

20

25

30

35

## FIELD EMISSION DISPLAY AND METHOD OF FABRICATING SAME

## ABSTRACT OF THE DISCLOSURE

A field emission display has a cathode, an emitter formed on the cathode, and an anode spaced apart from the cathode at a predetermined distance. The emitter includes an electron emission member having a longitudinal dimension, and an alignment member for aligning the electron emission member. The alignment member is formed with a magnetic material. The electron emission member is aligned by the alignment member such that the longitudinal dimension of the electron emission member is vertically extended from the cathode toward the anode. The electron emission member may be formed with carbon fibers or graphite particles. The magnetic material is coated on the surface of the carbon fibers or incorporated into the internal structure of the carbon fibers.

CAG/ej

EJ PAS275569.1-\* -9/23/00 2:41 PM